APPLICANT(S): BARTLETT, Philip Nigel et al.

SERIAL NO.: 10/538,769 FILED: June 10, 2005

Page 2

## AMENDMENTS TO THE CLAIMS

Please amend claim 18

The following listing of claims replaces all versions, and listings, of claims in this application.

## Listing of Claims:

 (Previously Presented) A portable electronic device comprising an electrochemical cell, said cell comprising a positive electrode, a negative electrode and an electrolyte.

wherein said positive electrode comprises a mesoporous structure having a periodic arrangement of substantially uniformly sized pores with a diameter in the order of  $10^{-9}$  to  $10^{-8}$  m.

wherein said mesoporous structure comprises a metal oxide, hydroxide or oxyhydroxide selected from the group consisting of gold oxide, palladium oxide, nickel oxide (NiO), nickel hydroxide (Ni(OH)<sub>2</sub>), nickel oxy-hydroxide (NiOOH) and ruthenium oxide, and

wherein said negative electrode comprises a material that is carbon or palladium.

- 2. (Canceled)
- 3. (Previously Presented) A portable electronic device according to claim 1, wherein the mesoporous structure of the positive electrode additionally comprises a metal, wherein said metal oxide, metal hydroxide or metal oxy-hydroxide forms a surface layer over said metal and extends over the pore surfaces.
- (Previously Presented) A portable electronic device according to claim 1, wherein the
  mesoporous structure of the positive electrode comprises a metal that is nickel or nickel
  alloys.
- 5-6. (Canceled)
- 7. (Previously Presented) A portable electronic device according to claim 1, wherein the mesoporous structure has a pore number density of about 4x10<sup>11</sup> to 3x10<sup>13</sup> pores per cm<sup>2</sup>.

APPLICANT(S): BARTLETT, Philip Nigel et al. SERIAL NO.: 10/538,769

FILED:

June 10, 2005

Page 3

8. (Previously Presented) A portable electronic device according to claim 1, wherein at least 85 % of the pores in said mesoporous structure have pore diameters within 30 % of the average pore diameter.

- (Previously Presented) A portable electronic device according to claim 1, wherein the
  mesoporous structure has a hexagonal arrangement of pores that are continuous through the
  thickness of the electrode
- 10. (Previously Presented) A portable electronic device according to claim 9, wherein the hexagonal arrangement of pores has a pore periodicity in the range of 5 to 9 nm.
- 11. (Previously Presented) A portable electronic device according to claim 1, wherein the negative electrode comprises a mesoporous structure having a periodic arrangement of substantially uniformly sized pores with a diameter in the order of 10<sup>-9</sup> to 10<sup>-8</sup> m.
- 12. (Previously Presented) The portable electronic device of claim 1, wherein said mesoporous structure is a film having a thickness in the range of about 0.5 to about 5 micrometers.
- 13-14. (Canceled)
- 15. (Previously Presented) The portable electronic device of claim 1, wherein said mesoporous structure comprises nickel and a nickel oxide, a nickel hydroxide or a nickel oxy-hydroxide that is NiO, Ni(OH)<sub>2</sub> and NiOOH, said nickel oxide, nickel hydroxide, or nickel oxy-hydroxide forming a surface layer over said nickel and extending over the pore surfaces, and wherein said negative electrode has a mesoporous structure comprised of carbon or palladium.
- 16. (Previously Presented) The portable electronic device of claim 15, wherein said negative electrode comprises nanoparticulate carbon.
- 17. (Previously Presented) The portable electronic device of claim 1, wherein said cell is constructed to function as a battery, as a supercapacitor or a combination thereof.
- 18. (Currently Amended) A portable electronic device according to elaim 6 claim 1, wherein the mesoporous structure has a pore diameter in the range of about 2.0-8.0 nm.

APPLICANT(S): BARTLETT, Philip Nigel et al.

SERIAL NO.: 10/538,769 FILED: June 10, 2005

Page 4

- 19. (Previously Presented) A portable electronic device according to claim 7, wherein the mesoporous structure has a pore number density of 1x10<sup>12</sup> to 1x10<sup>13</sup> pores per cm<sup>2</sup>
- 20. (Previously Presented) The portable electronic device of claim 8, wherein at least 85 % of the pores in said mesoporous structure have pore diameters to within 10 % of the average pore diameter.
- 21. (Previously Presented) The portable electronic device of claim 8, wherein at least 85 % of the pores in said mesoporous structure have pore diameters to within 5 % of the average pore diameter.
- 22. (Previously Presented) The portable electronic device of claim 4, wherein said Nickel alloys are alloys with a transition metal, nickel/cobalt alloys, iron/nickel alloys, cobalt, platinum, palladium or ruthenium.